

Mariner's Choice

Product Description

Never-Seez[®] Mariner's Choice is a heavy duty anti-seize and extreme pressure lubricant formulated to assure absolute parts protection against seizure, galling and corrosion in fresh and salt water environments.

Mariner's Choice offers unparalleled resistance to water washout and the best protection in continuous high moisture environments both above and below water lines.

Product Benefits

- Prevents seizure at temperatures up to 2,450°F (1,343°C)
- Prevents galvanic corrosion in salt and fresh water environments
- Superior resistance to water washout and water spray
- Excellent extreme pressure lubricating properties
- Low torque factor
- Compatible with soft metals
- Contains no copper

Product Applications

- Bilge pumps, screw shafts, prop shaft bearing housing, winches, cables, anchor lines, porthole studs, rigging and hoist cables
- Also, recommended for steel mills, suspension bridges, wind turbines, offshore rigging and other applications exposed to harsh salt water and fresh water conditions.

Limitations

- Not recommended for use in pure oxygen and/or oxygen rich systems.
- Not recommended for use in acidic environments. (Never-Seez High Temperature Stainless or Never-Seez Pure Nickel Special is suggested for these applications.)
- Never-Seez Mariner's Choice is NOT recommended for high speed bearing applications. (Never-Seez Red Bearing Lubricant is suggested for these applications.)
- In applications where indirect food contact is possible, use NSF H1 approved Never-Seez White Food Grade.

Directions

Apply liberally to all threaded areas of nuts and bolts. Before reapplication, clean threaded areas with a wire brush or mineral oil.

Other Anti-Seize Lubricants

- Regular Grade
- High Temp Bearing Lubricant
- High Temp Stainless
- Pipe Compound with Teflon[®]
- High Temp Stainless, Nuclear Certified
- Blue Moly Lubricant
- Black Moly
- Red Bearing Lubricant
- White Food Grade with PTFE
- Pure Nickel Special, Nuclear Grade
- Pure Nickel Special
- Heavy Metal Free

® Teflon is a Registered Trademark of Dupont.



Technical Specifications

Color	Black-Gray	
Temperature Range, °F (°C)	-297°F to 2,450°F (-183°C to 1,343°C)	
Thickener Type	Calcium Complex	
Particle Size, mil (microns)	3.5 maximum (75 µ)	
Density (g/cm ³)	1.31 to 1.39	
		ASTM Test Method
Flash Point, °F (°C)	>475°F (246°C)	D-92
Salt Fog Test, hrs.	4,000	B-117
Copper Corrosion Test @ 212°F (100°C), 24 hrs.	No Corrosion	D-130
Worked Penetration, 60 Strokes @ 77°F (25°C)	260-310	D-217
NLGI Grade	1/2	D-217
Dropping Point, °F (°C)	572 (300)	D-566
Torque Coefficient, k factor	0.11	
Water Washout, % loss @ 100°F	<1.00	D-1264
@ 175°F	<2.75	
Bearing Rust Test	Pass	D-1743
Four Ball EP	Load Wear Index	127.3
	Last Non-Seizure Load (scar)	100 kgf (0.45 mm)
	Last Seizure Load (scar)	620 kgf (2.21 mm)
	Weld Load	800 kgf
Fretting Wear @ 73°F (23°C), 22 hrs., mg loss	7.15	D-4170

Specifications: Tested to MIL-A-907E.

Ingredients: Proprietary Ingredients: Graphite (7782-42-5); Calcium fluoride (CaF₂) (7789-75-5); Zinc Oxide (1314-13-2); Aluminum (7429-90-5).
California Proposition 65: Alpha-Naphthylamine, beta-Naphthylamine

Shelf Life: Never-Seez Mariner's Choice compound does not deteriorate with age when stored unopened at temperatures below 120°F (49°C). Quality and performance are guaranteed for five years from the date of manufacture on unopened containers.

Use in accordance with Material Safety Data Sheet.

Ordering Information:

NEVER-SEEZ® MARINER'S CHOICE

STOCK NUMBER	DESCRIPTION	SIZE
NMCBT-8	Brush Top	8 oz.
NMCBT-16	Brush Top	16 oz.
NMC-42B	Pail	42 lb.
NMC-425B	Drum	425 lb.

Bostik, Inc.
211 Boston Street
Middleton, MA 1949-2128 USA
Technical Service: 888-603-8558
FAX: 978-750-7293
<http://www.bostik-us.com>

IMPORTANT NOTICE

All statements, technical information and recommendations set forth herein are based on tests which Bostik, Inc. believes to be reliable. However, Bostik, Inc. does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on Bostik's order acknowledgment. Bostik, Inc. warrants that the product conforms with Bostik's written specifications, and is free from defects. BOSTIK, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH THIS WARRANTY SHALL BE FOR THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK BE LIABLE FOR DIRECT, CONSEQUENTIAL ECONOMIC OR OTHER DAMAGES.